



# Bico Liner Plus

LINER GRADES • High Performance Liners



## Typical values

Property	Unit	Method	260	270	280	300	400
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>260</b>	<b>270</b>	<b>280</b>	<b>300</b>	<b>400</b>
Thickness	µm	ISO 534	360	375	390	420	555
Moisture average	%	Online	7,5	7,5	7,5	7,5	7,5
Bulk	cm <sup>3</sup> /g	ISO 534	1,38	1,39	1,39	1,40	1,39
Burst strength	kPa	ISO 2758	850	870	900	950	1130
SCT CD	kN/m	ISO 9895	4,35	4,55	4,65	5,30	7,10
Tensile stiffness CD	kN/m	ISO 1924-3	1030	1080	1100	1205	1530
Wax Pick (Dennison)	#	TAPPI T-549	18	18	18	18	18
Cobb 300s	g/m <sup>2</sup>	ISO 535	70	70	70	60	55
Roughness, Bendtsen	ml/min	ISO 8791-2	1300	1400	1400	1300	1400

## Guaranteed values

Property	Unit	Method	260	270	280	300	400
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>260</b>	<b>270</b>	<b>280</b>	<b>300</b>	<b>400</b>
Grammage average, min/max	%	ISO 536	+/-5	+/-5	+/-5	+/-5	+/-5

Typical values  
Guaranteed values  
Test conditions

Typical is what a customer can expect to receive on a customer reel average  
Guaranteed is a min/max value of a property on a customer reel average  
50% RH and 23°C

This product is also available in other grammages, if requested with a minimum of 25 tons

Internal code  
Issue date

May 2014

Latest updated version to be found on [www.dssmith.com/paper](http://www.dssmith.com/paper)

The Power of Less®

