



### Typical values

Property	Unit	Method	85	125	145
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>85</b>	<b>125</b>	<b>145</b>
Moisture average	%	Online	8,0	8,0	8,0
Burst strength	kPa	ISO 2758	210	300	360
CMT 30	N	ISO 7263	#	210	250
SCT CD	kN/m	ISO 9895	1,65	2,40	2,75
SCT MD	kN/m	ISO 9895	2,40	3,70	4,75
Tensile strength MD	kN/m	ISO 1924-3	4,60	6,50	10,70
Tensile strength CD	kN/m	ISO 1924-3	2,00	3,30	4,35
Scott Bond	J/m <sup>2</sup>	TAPPI T-569	250	250	250
Porosity, Gurley	sec	ISO 5636-5	30	30	30

### Guaranteed values

Property	Unit	Method	85	125	145
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>85</b>	<b>125</b>	<b>145</b>
Grammage average, min/max	%	ISO 536	+/-3	+/-3	+/-3
Moisture average	%	Online	8,0 +/-1	8,0 +/-1	8,0 +/-1
Burst strength, min	kPa	ISO 2758	170	250	300
CMT 30, min.	N	ISO 7263	#	180	210
SCT CD, min	kN/m	ISO 9895	1,45	2,15	2,45
Scott Bond, min	J/m <sup>2</sup>	TAPPI T-569	200	200	200
Porosity, Gurley, min	sec	ISO 5636-5	20	20	20
Cobb 1800s, max	g/m <sup>2</sup>	ISO 535	130	130	130

Typical values  
Guaranteed values  
Test conditions

Internal code  
Issue date

Typical is what a customer can expect to receive on a customer reel average  
Guaranteed is a min/max value of a property on a customer reel average  
50% RH and 23°C

3600  
January 2016

Latest updated version to be found on [www.dssmith.com/paper](http://www.dssmith.com/paper)