



Light Medium Plus

MEDIUM/FLUTING GRADES • Light Medium



Typical values

Property	Unit	Method	85	90
Grammage	g/m²	ISO 536	85	90
Moisture average	%	Online	8,0	8,0
SCT CD	kN/m	ISO 9895	1,65	1,70
SCT MD	kN/m	ISO 9895	2,80	3,10
Tensile strength MD	kN/m	ISO 1924-3	5,0	6,5
Tensile strength CD	kN/m	ISO 1924-3	2,2	1,8
Porosity, Gurley	sec	ISO 5636-5	30	25

Guaranteed values

Property	Unit	Method	85	90
Grammage	g/m²	ISO 536	85	90
Grammage average, min/max	%	ISO 536	+/-3	+/-3
Moisture average	%	Online	8,0 +/-1	8,0 +/-1
SCT CD, min	kN/m	ISO 9895	1,45	1,60

Typical values
Guaranteed values
Test conditions
Internal code
Issue date

Typical is what a customer can expect to receive on a customer reel average
Guaranteed is a min/max value of a property on a customer reel average
50% RH and 23°C
6010
June 2015
[Latest updated version to be found on www.dssmith.com/paper](http://www.dssmith.com/paper)

The Power of Less®

