



# Liner 2

LINER GRADES • Brown Liners



## Typical values

Property	Unit	Method	125	140
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>125</b>	<b>140</b>
Moisture average	%	Online	8,0	8,0
Burst strength	kPa	ISO 2758	360	400
SCT CD	kN/m	ISO 9895	2,30	2,60
SCT MD	kN/m	ISO 9895	3,40	3,70
Tensile strength MD	kN/m	ISO 1924-3	8,9	10,0
Tensile strength CD	kN/m	ISO 1924-3	2,9	3,3
Z-strength	kPa	ISO 15754	500	500
Porosity, Gurley	sec	ISO 5636-5	35	40
Cobb 60s	g/m <sup>2</sup>	ISO 535	35	35

## Guaranteed values

Property	Unit	Method	125	140
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>125</b>	<b>140</b>
Grammage average, min/max	%	ISO 536	+/-3	+/-3
Moisture average	%	Online	8,0 +/-1	8,0 +/-1
Burst strength, min	kPa	ISO 2758	340	380
SCT CD, min	kN/m	ISO 9895	2,00	2,30
Cobb 60s, max	g/m <sup>2</sup>	ISO 535	40	40

Typical values  
Guaranteed values  
Test conditions

Internal code  
Issue date

Typical is what a customer can expect to receive on a customer reel average  
Guaranteed is a min/max value of a property on a customer reel average  
50% RH and 23°C

3230  
June 2015

Latest updated version to be found on [www.dssmith.com/paper](http://www.dssmith.com/paper)

The Power of Less®

