



Typical values

Property	Unit	Method	120	130	135	165	170	185	215
Grammage	g/m²	ISO 536	120	130	135	165	170	185	215
Moisture average	%	Online	8,0	8,0	8,0	8,0	8,0	8,0	8,0
Burst strength	kPa	ISO 2758	280	300	310	379	390	414	456
SCT CD	kN/m	ISO 9895	1,90	2,00	2,10	2,62	2,70	2,92	3,33
SCT MD	kN/m	ISO 9895	3,40	3,70	3,80	4,46	4,60	4,87	5,49
Tensile strength MD	kN/m	ISO 1924-3	7,3	7,8	8,1	9,7	10,0	10,7	11,7
Tensile strength CD	kN/m	ISO 1924-3	2,4	2,6	2,7	3,3	3,4	3,7	4,4
Z-strength	kPa	ISO 15754	500	500	500	500	500	500	500
Porosity, Gurley	sec	ISO 5636-5	35	40	40	43	45	45	70
Cobb 60s	g/m ²	ISO 535	40	40	40	40	40	40	40

Guaranteed values

Property	Unit	Method	120	130	135	165	170	185	215
Grammage	g/m²	ISO 536	120	130	135	165	170	185	215
Grammage average, min/max	%	ISO 536	+/-3	+/-3	+/-3	+/-3	+/-3	+/-3	+/-3
Moisture average	%	Online	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1
Burst strength, min	kPa	ISO 2758	260	280	290	360	370	390	436
SCT CD, min	kN/m	ISO 9895	1,70	1,90	2,00	2,40	2,50	2,70	3,13
Friction (slip angle), min	°	TAPPIT-815	18	18	18	18	18	18	18
Cobb 60s, max	g/m ²	ISO 535	45	45	45	45	45	45	45

Typical values
Guaranteed values
Test conditions

Internal code
Issue date

Typical is what a customer can expect to receive on a customer reel average
Guaranteed is a min/max value of a property on a customer reel average
50% RH and 23°C

3300
June 2015

Latest updated version to be found on www.dssmith.com/paper