



## Typical values

| Property            | Unit                   | Method         | 105  | 120  | 130  | 150  |
|---------------------|------------------------|----------------|------|------|------|------|
| <b>Grammage</b>     | <b>g/m<sup>2</sup></b> | <b>ISO 536</b> |      |      |      |      |
| Moisture average    | %                      | Online         | 8,0  | 8,0  | 8,0  | 8,0  |
| CMT 30              | N                      | ISO 7263       | 180  | 200  | 210  | 240  |
| SCT CD              | kN/m                   | ISO 9895       | 1,90 | 2,10 | 2,30 | 2,50 |
| SCT MD              | kN/m                   | ISO 9895       | 2,80 | 3,40 | 3,70 | 4,50 |
| Tensile strength MD | kN/m                   | ISO 1924-3     | 5,1  | 7,3  | 7,9  | 6,1  |
| Tensile strength CD | kN/m                   | ISO 1924-3     | 1,9  | 2,4  | 2,6  | 2,3  |
| Porosity, Bendtsen  | ml/min                 | ISO 5636-5     | 260  | 280  | 280  | 340  |

## Guaranteed values

| Property                  | Unit                   | Method         | 105      | 120      | 130      | 150      |
|---------------------------|------------------------|----------------|----------|----------|----------|----------|
| <b>Grammage</b>           | <b>g/m<sup>2</sup></b> | <b>ISO 536</b> |          |          |          |          |
| Grammage average, min/max | %                      | ISO 536        | +/-3     | +/-3     | +/-3     | +/-3     |
| Moisture average          | %                      | Online         | 8,0 +/-1 | 8,0 +/-1 | 8,0 +/-1 | 8,0 +/-1 |
| CMT 30, min.              | N                      | ISO 7263       | 170      | 175      | 185      | 230      |
| SCT CD, min               | kN/m                   | ISO 9895       | 1,70     | 1,90     | 2,00     | 2,40     |

Typical values  
Guaranteed values  
Test conditions  
Internal code  
Issue date

Typical is what a customer can expect to receive on a customer reel average  
Guaranteed is a min/max value of a property on a customer reel average  
50% RH and 23°C

6010  
June 2015

Latest updated version to be found on [www.dssmith.com/paper](http://www.dssmith.com/paper)