



Typical values

Property	Unit	Method	100	105
Grammage	g/m²	ISO 536	100	105
Moisture average	%	Online	8,0	8,0
CMT 30	N	ISO 7263	165	170
SCT CD	kN/m	ISO 9895	1,75	1,80
SCT MD	kN/m	ISO 9895	2,70	2,80
Tensile strength MD	kN/m	ISO 1924-3	4,9	5,1
Tensile strength CD	kN/m	ISO 1924-3	1,8	1,9
Porosity, Gurley	sec	ISO 5636-5	30	35

Guaranteed values

Property	Unit	Method	100	105
Grammage	g/m²	ISO 536	100	105
Grammage average, min/max	%	ISO 536	+/-3	+/-3
Moisture average	%	Online	8,0 +/-1	8,0 +/-1
CMT 30, min.	N	ISO 7263	155	160
SCT CD, min	kN/m	ISO 9895	1,55	1,65

Typical values
Guaranteed values
Test conditions
Internal code
Issue date

Typical is what a customer can expect to receive on a customer reel average
Guaranteed is a min/max value of a property on a customer reel average
50% RH and 23°C

6000

June 2015

Latest updated version to be found on www.dssmith.com/paper