

White Bico 68

LINER GRADES • Presentation Liners



Typical values

Property	Unit	Method	210	240	280
Grammage	g/m²	ISO 536	210	240	280
Thickness	µm	ISO 534	280	319	375
Moisture average	%	Online	7,5	7,5	7,0
Bulk	cm ³ /g	ISO 534	1,33	1,33	1,34
Burst strength	kPa	ISO 2758	540	640	720
SCT CD	kN/m	ISO 9895	3,3	3,9	4,6
Tensile stiffness CD	kN/m	ISO 1924-3	770	880	1015
Roughness, Bendtsen	ml/min	ISO 8791-2	850	800	900
ISO Brightness - R457	%	ISO 2470-1	68	68	68

Guaranteed values

Property	Unit	Method	210	240	280
Grammage	g/m²	ISO 536	210	240	280
Grammage average, min/max	%	ISO 536	+/-5	+/-5	+/-5

Typical values
Guaranteed values
Test conditions

Typical is what a customer can expect to receive on a customer reel average
Guaranteed is a min/max value of a property on a customer reel average
50% RH and 23°C

This product is also available in other grammages, if requested with a minimum of 25 tons

Internal code
Issue date

May 2014

Latest updated version to be found on www.dssmith.com/paper