



# White Bico 75

LINER GRADES • Presentation Liners



## Typical values

Property	Unit	Method	
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>220</b>
Thickness	µm	ISO 534	290
Moisture average	%	Online	7,5
Bulk	cm <sup>3</sup> /g	ISO 534	1,32
Burst strength	kPa	ISO 2758	560
SCT CD	kN/m	ISO 9895	3,5
Tensile stiffness CD	kN/m	ISO 1924-3	810
Cobb 300s	g/m <sup>2</sup>	ISO 535	60
Roughness, Bendtsen	ml/min	ISO 8791-2	800
ISO Brightness - R457	%	ISO 2470-1	75

## Guaranteed values

Property	Unit	Method	
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>ISO 536</b>	<b>220</b>
Grammage average, min/max	%	ISO 536	+/-5

Typical values  
Guaranteed values  
Test conditions

Typical is what a customer can expect to receive on a customer reel average  
Guaranteed is a min/max value of a property on a customer reel average  
50% RH and 23°C

This product is also available in other grammages, if requested with a minimum of 25 tons

Internal code  
Issue date

May 2014

Latest updated version to be found on [www.dssmith.com/paper](http://www.dssmith.com/paper)

The Power of Less®

